



# VERISAFE

Standard and Fire Resistant Environmental Plastics

	<b>TECHNICAL SPECIFICATIONS</b>	
	<b>VERISAFE® B1 280</b>	

<b>Product:</b>	Film 7000 mm 280 $\mu$ , white Folded in 4 print : Verisafe B1 280/LPS logo 30 rolls per pallet	<b>Reference:</b>	VERISAFE B1 280
<b>Type:</b>	AL80FB1	<b>Structure:</b>	Mono-extruded
<b>Presentation:</b>	rolls of 15 lm	<b>Shrinkage:</b>	Bi-oriented

PROPERTIES	SPECIFICATIONS	UNIT	NORM
Closed width	1775 -0 +60	mm	ISO 4592
Gusset	862.5 $\pm$ 40	mm	ISO 4592
1/2 perimeter	3500 -0 +120	mm	ISO 4592
Average thickness	280 $\pm$ 5 %	my	ISO 4591
Spot thickness	280 $\pm$ 15 %	my	ISO 4593

Coefficient of friction	0.30 $\leq$ Kd $\leq$ 0.40		ISO 8259
Tensile stress at break SL (MD)	$\geq$ 17	Mpa	ISO 527-3
ST (TD)	$\geq$ 15	Mpa	ISO 527-3
Elongation at break SL (MD)	$\geq$ 490	%	ISO 527-3
ST (TD)	$\geq$ 480	%	ISO 527-3
Dart DropTest	$\geq$ 650	gr	ISO 7765 - 1/2
Corona treatment - 1 side tube	$\geq$ 38	mN/m	NF T 54 - 124
Opacity	$\geq$ 70		
Grade	0.30 $\pm$ 0.15	g/10 min	ISO 1133
Density	0,998 $\pm$ 0.008	g/cm <sup>3</sup>	ISO 1183

Date: 11 March 2008

<b>Solicom sa</b>	Tel: +352 26 95 72 56
Rue de Drinklange 9	Fax: +352 26 95 80 56
L - 9911 Troisvierges	<a href="mailto:info@solicompack.com">info@solicompack.com</a>